

## Filo acciaio al carbonio e basso legato

|                                       | C        | Mn   | Si   | Cu        | Mo   | Cr   | Ni   |
|---------------------------------------|----------|------|------|-----------|------|------|------|
| AWS A5.18 - EN440 ER70S-6 G3Si1       | 0.07     | 1.40 | 0.80 | max 0.030 |      |      |      |
| AWS A5.18 - EN440 ER70S-6 G4Si1       | 0.07     | 1.70 | 0.50 | max 0.030 |      |      |      |
| AWS A5.28 - 96 EN12072 - 95 ER80S - G | 0.08     | 1.70 | 0.50 |           | 0.50 | 0.50 | 1.50 |
| AWS A5.28 - 96 - ER100 SG             | max 0.07 | 1.40 | 0.70 | max 0.030 | 0.20 | 0.50 | 0.60 |
| AWS A5.28 - 96 - ER100 S1             | 0.08     | 1.60 | 0.60 | max 0.30  | 0.30 | 0.50 | 1.50 |

## Filo acciaio inossidabile

| AWS ER | Werkstoff Nr | BS 2901 | C    | Si  | Mn   | Cr   | Ni   | Mo  | Other       |
|--------|--------------|---------|------|-----|------|------|------|-----|-------------|
| 307Si  | 1.4370       | -       | 0.07 | 0.8 | 7    | 18   | 8    | -   | -           |
| 308LSi | 1.4316       | 308S93  | 0.02 | 0.8 | 1.75 | 20   | 10   | -   | -           |
| 309LSi | 1.4332       | 309S92  | 0.02 | 0.8 | 1.8  | 23.5 | 13.5 | -   | -           |
| 309LMo | 1.4459       | -       | 0.02 | 0.4 | 1.5  | 21.5 | 12.5 | 2.7 | -           |
| 310L   | 1.4335       | -       | 0.2  | 0.3 | 1.8  | 24.5 | 20.5 | -   | -           |
| 312    | 1.4337       | 312S94  | 0.1  | 0.4 | 1.8  | 30   | 9.5  | -   | -           |
| 316LSi | 1.4430       | 316S93  | 0.02 | 0.8 | 1.8  | 18.5 | 12.5 | 2.7 | -           |
| 317L   | 1.4438       | 317S96  | 0.02 | 0.4 | 1.8  | 19   | 13.5 | 3.6 | -           |
| 318    | 1.4576       | 318S96  | 0.04 | 0.4 | 1.8  | 19.5 | 11.5 | 2.7 | 12C<Nb<0.75 |
| 347Si  | 1.4551       | 347S96  | 0.04 | 0.8 | 1.8  | 19.5 | 9.5  | -   | 12C<Nb<1.00 |

## Filo alluminio

| DIN 1732       | AL 99.5        | AL MG 3   | AL MG 5   | AL SI 5  | AL SI 12  | AL MG 4.5 MN | AL MG 5 MnZr |
|----------------|----------------|-----------|-----------|----------|-----------|--------------|--------------|
| AWS ASTM       | ER 1100        | 5154 A    | 5356      | 4043     | 4047      | 5183         | 5087         |
| BS 2901 PT4    | 1050 A         | 5154 A    | 5356      | 4043     | 4047      | 5183         | 5087         |
| SI             | 0.25           | 0.25      | 1.8       | 4.50-6.0 | 11.0-13.0 | 0.40         | 0.25         |
| FE             | 0.40           | 0.40      | 0.40      | 0.60     | 0.80      | 0.40         | 0.40         |
| CU             | 0.05           | 0.05      | 0.10      | 0.30     | 0.30      | 0.10         | 0.05         |
| MN             | 0.05           | 0.50      | 0.05-0.20 | 0.05     | 0.15      | 0.60-1.0     | 0.7-1.1      |
| MG             | 0.05           | 3.10-3.90 | 4.50-5.50 | 0.05     | 0.10      | 4.30-5.20    | 4.5-5.2      |
| CR             | -              | 0.25      | 0.05-0.20 | -        | -         | 0.05-0.25    | 0.05-0.25    |
| ZN             | 0.07           | 0.20      | 0.10      | 0.10     | 0.20      | 0.25         | 0.25         |
| TI             | 0.05/0.10-0.20 | 0.20      | 0.06-0.20 | 0.20     | -         | 0.20         | 0.15         |
| Other elements | each           | 0.05      | 0.05      | 0.05     | 0.05      | 0.05         | 0.05         |
|                | total          | 0.15      | 0.15      | 0.15     | 0.15      | 0.15         | 0.15         |
| Aluminium      | 99.5% min.     | resto     | resto     | resto    | resto     | resto        | resto        |

## Filo per rame e sue leghe

|         | CU | AL | SN | SI | DIN      | AWS         | BS  |
|---------|----|----|----|----|----------|-------------|-----|
| AL BZ 8 | 92 | 8  | -  | -  | 1733.T 1 | Er Cu al-A1 | C28 |
| CU SN 6 | 94 | -  | 6  | -  | 1733.T 1 | Er Cu Sn A  | C11 |
| CU SN   | 99 | -  | 1  | -  | 1733.T 1 | Er Cu       | C7  |
| CU Si 3 | 97 | -  | -  | 3  | 1733.T 1 | Er Cu Si A  | C9  |